

Excellent Integrated System Limited

Stocking Distributor

Click to view price, real time Inventory, Delivery & Lifecycle Information:

[Daburn](#)


[ST250-1 BLK](#)

For any questions, you can email us directly:

sales@integrated-circuit.com



Daflex Stretch-N-Seal Rubber Non-Heat Shrink Tape



Description: DAFLEX ST250 cold shrinking Stretch-N-Seal tape requires no heat to provide a secure covering where the size and or shape of an object does not permit the use of shrinkable tubing. Simply remove 2" to 3" of tape from the roll, remove the liner, stretch tape to 50% of the supplied width and wrap it spirally around the object , with a 50% overlap. In minutes the tape will react with itself to form a mass which will provide protection from moisture, most chemicals, over 1KV per mil and will operate from -40°C to 130°C.

U/L Recognized: 100°C; Weather Resistant; Cold Resistant.

DAFLEX ST250 can be removed easily without leaving any residue, since the tape does not use a mastic or adhesive liner. Shelf-life is over 5 years. It is helpful for covering, sealing, splicing, holding bundles, joining and repair applications.

DABURN Cat. No.	Nominal Width	Nominal Thickness	Ft. / Roll	Color	Click to Order Prototype Quantities
ST250-1	1"	.018"	15	BLACK	Order
ST250-1	1"	.018"	15	WHITE	Order
ST250-1A	1"	.018"	8	BLACK	Order
ST250-2	3/4"	.018"	30	BLACK	Order

Operating Temperature: -10°C to +130°C

U/L Recognized: 100°C; Weather Resistant; Cold Resistant.

Properties of DAFLEX Stretch-N-Seal Rubber Tape

Series ST250	Test Method	Results
Heat Resistance	ASTM-D3391-75	130°C PASS
Dielectric Breakdown	ASTM-D4325-83	1060V/mil @ 21°C, 38% R.H.
Tensile Strength	ASTM-D3391-75	1000 psi
Ultimate Elongation	ASTM-D3391-75	560%

Chemical Resistance	Acetone, Ethylene Glycol, Ethanol, Methanol, Ozone, Water	Excellent
	Diethyl Phthalate, Methyl Ethyl Ketone	Good
	Machine Oil	Fair
	Gasoline, Hexane, Toluene	Poor

Back to [Hot New Products](#).

Back to DABURN'S [Home Page](#).

Daburn electronics & cable corp.

224 Pegasus Ave.

Northvale, NJ 07647

Tel: 201-768-5400

Fax: 201-768-9642

E-Mail: daburn@daburn.com

URL: <http://www.daburn.com/>